

to be identified as the start to superconductive cooperative phenomena in the isolated grains. It should be noted that in granular Al, Cooper pairs in coupled grains have been shown to exist already at a point where $\rho(T)$ upon cooling has decreased by only 20% of its highest value. This has been proven qualitatively [19] and more recently also quantitatively [20] by the negative frequency shift occurring in a microwave cavity. In 100 Å films, a shoulder in the frequency shift owing to 2D fluctuations was observed above the T_c of the grains. In our Ba-La-Cu-O system, a series of layer-like phases with considerable variety in compositions are known to exist [16, 21], and therefore 2D correlations can be present.

The granularity of our system can be justified from the structural information, and more quantitatively from the normal conductivity behaviour. From the former, we know that more than one phase is present and the question arises how large are the grains. This can be inferred from the logarithmic fingerprint in resistivity. Such logarithmic increases are usually associated with beginning of localization. A most recent example is the Anderson transition in granular Sn films [22]. Common for the granular Sn and our samples is also the resistivity at 300 K, lying in the range of 0.06 to 0.02 Ωcm , which is near the microscopic critical resistivity of $\rho_c = 10 L_0 \hbar/e^2$ for localization. From the latter formula, an interatomic distance L_0 in the range of 100 Å is computed, thus a size of superconducting grains of this order of magnitude must be present. Upon cooling below T_c , Josephson junctions between the grains phase-lock progressively [23] and the bulk resistivity gradually drops to zero by three orders of magnitude, for sample 2 (Fig. 1). At larger current densities, the weaker Josephson junctions switch to normal resistivity, resulting in a temperature shift of the drop, as shown in Fig. 3. The plateau in resistivity occurring below the 80% drop (Fig. 1) for the higher current density of 0.5 A/cm², and Fig. 2 curve (c) may be ascribed to switching of junctions to the normal state.

The way the samples have been prepared seems to be of crucial importance: Michel et al. [21] obtained a single-phase perovskite by mixing the oxides of La and Cu and BaCO₃ in an appropriate ratio and subsequent annealing at 1,000 °C in air. We also applied this annealing condition to one of our samples, obtained by the decomposition of the corresponding oxalates, and found no superconductivity. Thus, the preparation from the oxalates and annealing below 950 °C are necessary to obtain a non-perovskite-type phase with a limited temperature range of stability exhibiting this new behaviour. The formation of this phase at comparatively low temperatures is favoured by the intimate mixture of the compo-

nents and the high reactivity of the oxalates owing to the evolution of large amounts of H₂O and CO₂ during decomposition.

IV. Conclusion

In the concentration range investigated, compounds of the Ba-La-Cu-O system are metallic at high temperatures, and exhibit a tendency towards localization upon cooling. Samples annealed near 900 °C under reducing conditions show features associated with an onset of granular superconductivity near 30 K. The system consists of three phases, one of them having a metallic perovskite type layer like structure. The characterization of the new, apparently superconducting, phase is in progress. An identification of that phase may allow growing of single crystals for studying the Meissner effect, and collecting specific-heat data to prove the presence of high T_c bulk superconductivity.

The authors would like to thank H.E. Weibel for his help in getting familiar with the conductivity measurement system, E. Courtens and H. Thomas for discussions and a critical reading of the manuscript.

References

1. Tinkham, M., Beasley, M.R., Larbalestier, D.C., Clark, A.F., Finnemore, D.K.: Workshop on Problems in Superconductivity, Copper Mountain, Colorado, August 1983, p. 12
2. Beasley, M.R., Gehalle, T.H.: Phys. Today 36 (10), 60 (1984)
3. Müller, J.: Rep. Prog. Phys. 43, 663 (1980)
4. Ott, H.R.: Unconventional Superconductivity. Zürich Phys. Soc. Seminar, Zürich, February 13, 1986
5. Johnston, D.C., Prakash, H., Zachariassen, W.H., Viswanathan, R.: Mat. Res. Bull. 8, 777 (1973)
6. Baratoff, A., Binnig, G.: Physics 108 B, 1335 (1981)
7. Baratoff, A., Binnig, G., Bednorz, J.G., Gervais, F., Scriver, J.L.: In: Superconductivity in *d*- and *f*-Band Metals, Proceedings IV Conference in 'Superconductivity in *d*- and *f*-Band Metals', Buckel, W. and Weber, W. (eds), p. 419, Kernforschungszentrum Karlsruhe 1982
8. Binnig, G., Baratoff, A., Hönig, H.E., Bednorz, J.G.: Phys. Rev. Lett. 45, 1352 (1980)
9. Sleight, A.W., Gillson, J.L., Bierstedt, F.E.: Solid State Commun. 17, 27 (1975)
10. Datlogg, B.: Physica 126 B, 275 (1984)
11. Thanh, T.D., Koma, A., Taraka, S.: Appl. Phys. 22, 205 (1980)
12. Mattheis, F., Hamann, D.R.: Phys. Rev. B 26, 2682 (1982); *ibid.* 28, 4227 (1983)
13. Chakraverty, B.K.: J. Phys. Lett. 40, L99 (1979), J. Phys. 42, 1351 (1981)
14. Höck, K.-H., Nickisch, H., Thomas, H.: Helv. Phys. Acta 56, 237 (1983)
15. Englmann, R.: In: The Jahn-Teller Effect in Molecules and Crystals. London, New York: Wiley Interscience 1972
16. Goodenough, J.B., Longo, M.: Magnetic and other properties of oxide and related compounds. In: Landolt-Boernstein New